

BONDING TILE DIRECTLY TO ORIENTED STRAND BOARD (OSB)

Wood-based panels like Oriented Strand Board (OSB) expands and contracts with changes in moisture content. Therefore, according to the 2012 TCNA Handbook, they are not recommended as a substrate material for direct bonding of ceramic or natural stone tile with cement mortars. Plywood manufactured with a fully waterproof adhesive and with an exposure durability rating of Exposure 1 or Exterior may be used on interior, residential, horizontal surfaces when installed in accordance with ANSI A108.1 Article 3.4, for direct bonding.

OSB panels are manufactured under the provisions of APA PRP-108 or PS 2-92 and are comprised of soft, thin wood strands or chips, which are held together with waterproof adhesives. Plywood panels are thin veneers of wood glued together to form the desired panel thickness. Although both panels perform well from a structural standpoint, it is the surface of each which must be considered for direct bonding of ceramic tile. OSB will change dimensionally as the moisture in the environment and board changes. This regular expansion and contraction with changes in the environmental humidity will weaken the bond of a cement mortar to the OSB surface. Exterior grade plywood is an acceptable substrate because the latex or polymer-modified mortar is bonding directly to a continuous wood surface.

In cases where OSB is to be used as an underlayment on interior floor installation it must be properly treated before the installation of tile. If direct bonding of the ceramic tile to the OSB is required, a membrane must be installed on the OSB, before ceramic tile installation, that will compensate for the movement in the OSB due to changes in the moisture content. Custom® Building Products RedGuard® Waterproofing and Crack Prevention Membrane applied at 30 mils wet film thickness will provide the needed protection. As a waterproofing agent CUSTOM's RedGuard will protect the OSB from moisture in the thin set mortar and subsequent surface exposure. As an anti-fracture membrane CUSTOM's RedGuard will prevent any movement in the OSB from transferring to the tile assembly. Once the RedGuard is dry, tile can be safely installed to the RedGuard coated OSB with one of CUSTOM's polymer modified thin set or medium bed mortars.

Note: OSB must be protected from water or moisture exposure during shipping and through out the installation process. The underside of an OSB subfloor must be properly protected from moisture to prevent the sheets from warping.

The information in this bulletin is presented in good faith, but no warranty, express or implied, is given nor is freedom from any patent in as much as any assistance furnished by CUSTOM with reference to the safe use and disposal of its products provided without charge. Custom Building Products assumes no obligation or liability therefore, except to the extent that any such assistance shall be given in good faith.



Technical Bulletin
Technical Services 800-282-8786
custombuildingproducts.com