

Jamoblend Floor & Wall Sanded Thin-Set Mortar

1 Product Name

Jamoblend Floor & Wall Sanded Thin-Set Mortar

2 Manufacturer

Custom Building Products
 Technical Services
 10400 Pioneer Boulevard, Unit 3
 Santa Fe Springs, CA 90670
 Customer Support: 800-272-8786
 Technical Services: 800-282-8786
 Fax: 800- 200-7765
 Email: contactus@cbpmail.net
custombuildingproducts.com

3 Product Description

JAMOBLEND is an economical, sanded thin-set for most tile installations, with good working time to apply and adjust tiles. Meets ANSI A118.1. Meets ANSI A118.4 with STAR-SET® 1000 LATEX ADDITIVE added.

Uses

JAMOBLEND is to be used as a bond coat for setting non-absorptive and semi-vitreous ceramic tile in residential or commercial installations. JAMOBLEND is an excellent water and impact-resistant dry set mortar, which is also water cleanable and nonflammable. JAMOBLEND is good for interior and exterior work and requires no soaking of tiles. JAMOBLEND will not be affected by prolonged contact with water. It provides a permanent installation with higher bond strength with lower material and labor costs than conventional Portland cement mortar beds.

Suitable Substrates

Suitable backings, when properly prepared, are plumb and true masonry, concrete, gypsum board (dry areas only), WonderBoard® Backerboard, cured Portland cement mortar beds, brick, ceramic tile and marble.

Limitations to the Product

JAMOBLEND must not be used directly over wood, asphalt sheeting, vinyl covered wallboard, Masonite®, cement asbestos board, painted surfaces, metal, glass or plastic. Use in temperature ranges above 40° F (4.5° C). Protect from freezing for the first 72 hours.

4 Technical Data

Technical Chart

Technical Data

	Typical Value
Open Time @ 70° F (21° C)	>55 minutes
Adjustability @ 70° F (21° C)	>45 minutes
Shear Bond Strength	
Non-Vitreous Tile: 7 day dry cure	>200 psi (14.1 kg/cm ²)
28 day dry cure	>250 psi (17.6 kg/cm ²)
Vitreous Tile: 7 day dry cure	>160 psi (11.2 kg/cm ²)
28 day dry cure	>190 psi (13.4 kg/cm ²)



5 Instructions

General Surface Prep

All surfaces on which tile is to be set must be dry, structurally sound, free of any dirt or curing compounds. For use over existing ceramic tile, scarify surface of tile then prime with Jamo STAR BOND. Additional installation procedures may be found in the TCA Handbook.

Mixing Procedures

Add the contents of the bag to approximately 1-1/4 gallons (4.7 L) of clean water suitable for drinking, or if desired, Jamo STAR-SET 1000. Mix thoroughly and let stand for 15 minutes then remix before using. Mortar should be of a thick, trowelable consistency. If a mechanical mixer is to be used, it must be done at a low RPM (150) so as not to entrap air into the mortar. Do not add water, latex, or additional powder after slaking period.

Application of Product

Remove any dirt or other foreign material from the area to be tiled. With pressure, apply a skim coat on the substrate using the flat side of the trowel. With a notch trowel, immediately apply a heavier coat of material leaving enough mortar to provide 100% coverage to the back of the tile. The mortar bed should be 3/16" (4.8 mm) thick after beat in. With high lug tile, back buttering may be required to ensure 100% coverage to the back of the tiles. For best results, cover only a small area at a time with this mix. Then immediately cover this with tile and beat in the tile. Once initial set has taken place, do not vibrate or beat the tile or its backing.

Curing of Product

A minimum cure will be obtained in 12 - 24 hours depending on ambient temperatures and humidity. Normal grouting should be done 24 hours after initial set.

Cleaning of equipment

Water will remove uncured mortar from the tile surface or tools.



CUSTOM®

Jamoblend Floor & Wall Sanded Thin-Set Mortar

Health Precautions

May cause eye, skin or lung injury. Contains free silica. Prolonged exposure to dust may cause delayed lung disease (silicosis). May cause cancer based on animal data. Eliminate exposure to dust. Use NIOSH approved dust mask for silica dust. Contains Portland cement. If any cement or cement mixture gets into eyes, flush immediately and repeatedly with water, and consult physician promptly. Fresh mixed cement, mortar, concrete, or grout may cause skin injury. Avoid contact with skin where possible and wash exposed skin areas promptly with water. KEEP OUT OF REACH OF CHILDREN.

6 Availability & Cost

Item Code	Color	Size	Package
131131	Grey	50 pounds (22.68 kg)	Bag
131001	White	50 pounds (22.68 kg)	Bag

7 Product Warranty

Seller warrants that should this product prove to be defective material, it will replace the same or refund the purchase price of the goods. THIS WARRANTY IS IN PLACE OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED. WARRANTIES OF MERCHANTABILITY AND OF FITNESS ARE HEREBY DISCLAIMED. The suitability of a product for an intended use shall be solely up to the user. Seller assumes no liability for consequential damages. Its liability shall in no event exceed the purchase price of the materials supplied by it. No person has the authority to change these items and there are no warranties except as herein stated.

Jamoblend Floor & Wall Sanded Thin-Set Mortar

8 Coverage

Approximately 85 – 95 sq. ft. per 50 lb. bag (7.9 – 8.8 M2 per 22.68 kg) when applied with a 1/4" x 1/4" x 1/4" (6 x 6 x 6 mm) square-notch trowel.

