1 Product Name

CEG-Lite™ 100% Solids Commercial Epoxy Grout

2 Manufacturer

Custom Building Products
Technical Services
10400 Pioneer Boulevard, Unit 3
Santa Fe Springs, CA 90670
Customer Support: 800-272-8786
Technical Services: 800-282-8786

Fax: 800- 200-7765

Email: contactus@cbpmail.net custombuildingproducts.com

3 Product Description

CEG-Lite™ 100% Solids Commercial Epoxy Grout provides chemical and stain resistance with a fast cure time for a quick return to service. Its lightweight formula makes it easier to spread than typical epoxy grouts and is water-cleanable. CEG-Lite exceeds ANSI A118.3 performance requirements, is suitable for use on vertical joints without an additive, and can also be used as a mortar. Its two-component formula combines a Part A pigmented hardener with a Part B consisting of resins and lightweight aggregates. CEG-Lite is compatible with both CEG-Lite Part A and CEG Part A epoxy grout color pigment and hardener products. Formula is patent-pending.

Key Features

- · Color consistent, stain and chemical resistant
- · Easy to spread and clean-up
- No sagging in vertical joints
- · Contains recycled LEED contributing materials

Uses

- CEG-Lite can be used as both a grout and as a setting mortar
- Use with virtually any tile vitreous, semi-vitreous or impervious tile including ceramic, mosaic, quarry, pavers, cement, porcelain, glass, brick, mini-brick, precast terrazzo and natural stone, including green marble
- Use to fill joint widths from 1/16" to 1/2" (1.6 13 mm)
- May be used for both floor and wall installations
- Interior and exterior applications. When used as a grout on exterior applications, color variations may occur over time.
- Countertops, backsplashes, tub and shower areas, sunken tile tubs and swimming pools that are continually wet
- For use in areas requiring chemical resistance. For installations with high chemical resistance requirements, see chemical resistance chart for details.
- For commercial kitchens that may use harsh chemical cleaners and for installations in industrial settings, CUSTOM recommends <u>CEG-IG 100%</u> <u>Solids Industrial Grade Epoxy Grout</u>.

Suitable Substrates (when used as a bonding mortar)

- Plumb and true masonry, concrete, cured Portland cement mortar beds
- Bonds directly to brick, ceramic tile, cementitious backer units, steel, glass and fiberglass



Composition of Product

2-part formula, with Part A pigmented liquid epoxy hardener and Part B liquid epoxy resin combined with aggregates.

Benefits of Product in the Installation

- 2-Part 100% Solids Epoxy
- No shrinkage
- · Color consistent and stain resistant
- Does not require sealing
- · Easy to spread and water clean-up
- · No additive needed for critical grouting applications
- Contains recycled materials that may contribute to LEED® credits
- Exceeds ANSI A118.3 (100% Epoxy) performance requirements



Limitations to the Product

- Should not be used in an environment with temperature requirements above 250°F (121°C) for any extended period of time.
- When used to install tile in an area that will be continually wet (e.g. swimming pools, gang showers, etc.), it is recommended that the complete installation be cured 14 days prior to full submersion with chemically treated water.
- Epoxy, epoxy residue, or wash water will discolor painted or anodized surfaces upon contact. Protect these surfaces from exposure.
- Should be tested for possible staining or slight color changes when used with porous, absorptive, textured tile and stone units such as rough textured ceramic tile, natural stone or marble.
- All epoxies are temperature sensitive. Epoxies are easiest to apply
 when temperatures are between 70°F and 85°F (21°C and 29°C).
 Lower temperatures will cause the epoxy to become stiff and more
 difficult to work and will extend initial set. Higher temperatures will
 cause the epoxy to become more fluid and will accelerate the set.
- With all epoxies, a crystallization effect can occur when the liquid gets below 45°F (7°C) and/or has experienced multiple cycles of high and low temperature changes. If material is hard, place the sealed container (with the lid on), in warm tap water at approximately 120°F (49°C) for 10 to 20 minutes, and when re-liquified, let the material return to room temperature before mixing.
- Colors may be slightly different than shown on color samples. When
 color considerations are critical, a mock-up should be constructed prior
 to final selection and application.
- Not recommended in some manufacturing facilities where strong solvents are used. Consult Technical Services on questionable installations. CUSTOM recommends the use of <u>CEG-IG™ Commercial</u> <u>Epoxy Grout</u> for these installations.
- The use of non-rinse, enzyme-based cleaners is not recommended because they will break down the organic materials in epoxy grout, causing permanent damage.
- Some ceramic, glass, metal, marble or stone tiles can be scratched or damaged by the silica aggregate filler. Perform a test on a small area prior to use. <u>Polyblend® NonSanded Grout</u> may be appropriate for joints smaller than 1/8" or for tile not suited for sanded grout.
- Not for use in movement joints or changes of plane in the tile installation. In these areas us an appropriate caulk or sealant such as <u>Commercial 100% Silicone Caulk</u> or <u>Polyblend® Ceramic Tile Caulk</u>

Packaging

Grout mixture requires two separately-sold parts:

- Part A 1.3 lb (.58 kg) container of pigmented liquid epoxy hardener, available in 40 standard colors
- Part B 19 lb (8.6 kg) or 9.5 lb (4.3 kg) liquid epoxy resin combined with aggregates

4 Technical Data

Applicable Standards

Detailed installation procedures and use of epoxy mortars may be found in the TCNA Handbook under F-114, F-115, F-116E, F-125, F-128, F-143, F-131, F-132, F-134, F-135, F-200, F-205, TR-712 and TR-713 and in addition, in ANSI A108.6. Exceeds ANSI A118.3 specifications. Conforms to requirements for chemical-resistant, water cleanable tile setting and grouting epoxy found in ANSI A108.6 and ANSI A118.3.

Technical Chart

| Property | Test Method | Requirement | Typical Results | |
|------------------------------------|-----------------------|--------------|-----------------|--|
| Water Cleanability | A118.3 Section 5.1 | > 80 Minutes | >80 Minutes | |
| Initial Set | A118.3 Section 5.2 | > 2 Hours | >2 Hours | |
| Shrinkage | A118.3 Section 5.3 | < 0.25% | 0.08% | |
| Sag in Vertical Joints | A118.3 Section 5.4 | No Change | No Change | |
| Shear Bond Strength to Quarry Tile | A118.3 Section 5.5 | > 1000 psi | Pass | |
| Compressive Strength | A118.3 Section 5.6 | > 3500 psi | 5,800 psi | |
| Tensile Strength | A118.3 Section 5.7 | > 1000 psi | 1,700 psi | |
| Thermal Shock Resistance | A118.3 Section 5.8 | > 500 psi | 900 psi | |

Environmental Consideration

Custom® Building Products is committed to environmental responsibility in both products produced and in manufacturing practices. Use of this product can contribute towards LEED® v3 certification:

- Up to 2 points towards MR Credit 5, Regional Materials
- Up to 2 points towards MR Credit 4, Recycled Content
- Up to 1 point towards IEQ Credit 4.1, Low-Emitting Materials Adhesives & Sealants

Instructions

General Surface Prep

USE CHEMICAL-RESISTANT GLOVES, such as nitrile, when handling product.

All surfaces on which tiles are to be set must be dry, structurally sound, and not subject to temperatures below 65° F (18° C) or above 95° F (35° C). Surfaces must be dry and free of all grease, oil, dirt, dust, curing compounds, sealers, coating, efflorescence, old adhesive residues, gypsum-based underlayments and any other foreign matter.



NOTE: On porous or rough tiles, pre-grout sealing with a grout release such as <u>Aqua Mix Grout Release</u> or <u>TileLab SurfaceGuard</u> may be necessary to prevent staining. Try a test patch to be sure. Epoxy and epoxy wash residue should not be allowed to dry on painted, anodized and thin metal-plated surfaces. Clean uncured materials from these surfaces immediately with soap and water.

Bonding to Concrete Surfaces

In some applications, CEG-Lite™ may be used as a mortar when bonding to cement surfaces. Cleaning may be accomplished via mechanical abrasion, scraping or chipping. Smooth, steel- troweled concrete floors must be roughened to ensure a superior bond. Dry porous concrete should not be pre-dampened with water before applying CEG-Lite . Instead, skimcoat a thin layer of CEG-Lite first, then apply sufficient CEG-Lite with the appropriate notch trowel.

Bonding to Plywood Surfaces

In some applications, CEG-Lite™ may be used as a mortar when bonding to plywood surfaces. All wood flooring, when placed over conventional floor joist or other systems, should be of a design and thickness so as to meet ANSI A108.01. Further, the flooring to receive the CEG-Lite should be Exterior Grade Plywood only, secured with screw-type nails and glued where possible. A gap of 1/8" (3 mm) should be left between sheets of plywood and between the plywood edges and all materials which they abut to allow for expansion. These gaps should remain empty when the installation is complete. Do not force epoxy between edges of plywood sheets. Follow TCNA EJ-171 for expansion joint details. In addition, all wooden surfaces must be for interior use only and protected from exposure to water.

Miscellaneous Substrates

Other substrates like existing ceramic tile, steel, glass and fiberglass must all be free of all oils, coatings, dust and moisture. In addition, these surfaces should be roughened to ensure a good bond. It is also absolutely essential that the existing surface be structurally sound and firmly attached to the supporting structure.

Construction/Expansion/Control/Isolation Joints: Follow installation procedures as outlined in TCNA EJ-171.

Bonding to Existing Surfacing Material

Resilient flooring or plastic laminates must be well-bonded, as well as clean and free of all contaminates. Roughen the surface by sanding or scarifying; rinse and allow to dry. Do not sand flooring that contains asbestos. For existing well-bonded ceramic tile, mechanically abrade the surface. Rinse and allow to dry. When sanding, an approved respirator should be used.

Mixing Procedures

Open Part B and stir thoroughly to eliminate the effects of settling due to shipping. Add the entire contents of the pigment Part A to Part B and stir to produce a homogeneous consistency, eliminating any color streaks from appearing in the mixed unit. Do not mix partial units. Make sure to scrape bottom and sides of container during mixing.

NOTE: ONE PART A UNIT OF COLOR IS REQUIRED FOR ONE PART B RESIN COMPONENT FOR 1-GALLON UNIT; TWO PART A UNITS OF COLOR ARE REQUIRED FOR ONE PART B RESIN COMPONENT FOR THE 2-GALLON UNIT. GROUT WILL NOT HARDEN OR COME TO THE DESIRED COLOR IF INCORRECTLY MIXED. For best results, use a power mixer at 300 RPM or less to avoid entrapping air bubbles which cause pinholes in the grout. Do not overmix as this will cause the epoxy to flash set.

Application of Product

Application for Use as a Grout

Remove all grout from container and spread out in piles over the surface to be grouted as soon as mixing is completed. This will extend working time. When grouting walls, place epoxy on a mortarboard placed on the floor. Grout vertical surfaces as soon as possible after mixing. Apply grout using a hard epoxy rubber float, filling all joints full and even with surface of tile.

It is important to achieve 100% fill coverage with no voids in the joints to prevent pinholes and slumping of the epoxy grout. Remove excess epoxy by holding the grout float at a 90° angle and pulling the float diagonally across the grout joints using it like a squeegee. Removing as much epoxy as possible will make final cleaning easier. Avoid gouging joints. Do not allow epoxy to set on face of tile. Apply liberal amounts of clean, warm water over the grouted area. Adding a few drops (maximum) of dishwashing liquid to the water will aid in cleanup. Using a grout sponge and as little pressure as possible, work in a circular motion across tiles to loosen epoxy film and to finish the joints smoothly. Change rinse water (and sponge if buildup occurs) frequently to aid in cleanup and minimize epoxy residue left behind. As a final step, clean film from tile by dragging a damp, clean microfiber towel flatly across the tiles. Pot life (workability) of CEG-Lite will vary depending on ambient conditions. Pot life is approximately 60 minutes at 75° F (24° C).

Application for Use as a Mortar

Spread mixed epoxy with flat side of trowel onto substrate. Then, reapply additional mortar to a depth sufficient to be notched with a suitable trowel. Troweling should leave enough mortar to give minimum of 80% contact with back of the tile and a leave a mortar bed of about 3/32" (2.4 mm) for ceramic mosaic tile to 1/4" (6.3 mm) for quarry tile. Temperature affects set time; therefore, it is advisable to occasionally remove a tile to be sure mortar has not skinned over and sufficient transfer is being made. Approximate tack time is 30 minutes at 75°F (24°C). Pot life is approximately 60 minutes at 75°F (24°C). Should epoxy mortar get on surface of tile, it will be necessary to remove it with a damp sponge before it cures. Epoxy residue should not be allowed to cure on unintended surfaces (e.g. painted, wall papered, carpeted, wood, concrete, masonry and stucco surfaces).

NOTE: Do not use white lid Part B (new formula) with grey lid Part B (prior formula) on the same job. Also, do not mix white lid Part B (new formula) with the following prior formula CEG Part A colors: #135 - Mushroom, #10 - Antique White, #122 - Linen, #382 - Bone. Contact CUSTOM technical services for details.



Curing of Product

Available for light traffic after 7 hours with ambient temperature at 70° with 50% relative humidity; narrower grout joints and job site conditions may increase cure time. Because propane gas heaters will yellow epoxy, refrain from using such heaters or properly vent all exhaust during the curing process. Protect from harsh industrial cleaners for seven days and from aggressive chemicals for 14 days. Initial maintenance for the first seven days should be using clean water only. All grouting and cleaning should be completed within 80 minutes. If a grout haze is present on the tile, depending on the severity, use Aqua Mix NanoScrub alone or in conjunction with Aqua Mix Sealer & Coating Remover or Aqua Mix Non-Cement Grout Haze Remover. Mechanical scrubbing with the above cleaners can be used when necessary.

Exterior applications must be protected from rain, snow and other wet conditions for at least 7 days with

temperature above 50° F (10° C). If inclement weather is expected, protect the work area with tenting at least 1 foot (30 cm) above the finished surface to allow air flow. Enclose and protect exterior installations and maintain >50° F (10° C) temperatures for at least 72 hours for proper cure.

Protection

Chemical Resistance

| 28 Day Immersion at 23°C | | | | | |
|---|------|--|--|--|--|
| Acids (Organic and Mineral) | | | | | |
| Acetic Acid, 10% | | | | | |
| Citric Acid, 50% | | | | | |
| Lactic Acid, 10% | Pass | | | | |
| Tartaric Acid, 50% | | | | | |
| Tannic Acid 50% | Pass | | | | |
| 5% Benzoic acid | Pass | | | | |
| 5% Formic Acid | Pass | | | | |
| HCI, 36.5% | Pass | | | | |
| Nitric Acid, 30% | Pass | | | | |
| Phosphoric Acid 80% | Pass | | | | |
| Sulfuric Acid 50% | Pass | | | | |
| Alkalis | | | | | |
| Potassium Hydroxide, 45% | | | | | |
| Sodium Hydroxide Saturated | | | | | |
| Oxidizers/Bleach | | | | | |
| Sodium Hypochlorite, 5% | | | | | |
| 10% Potassium Permanganate | Pass | | | | |
| Hydrogen Peroxide | Pass | | | | |
| Water | | | | | |
| Mineral water | | | | | |
| Sea water | Pass | | | | |
| Solvents | | | | | |
| Ethanol | Pass | | | | |
| Mineral Spirits | Pass | | | | |
| Methanol | Pass | | | | |
| Isopropanol | Pass | | | | |
| Cleaners | | | | | |
| Aqua Mix Heavy Duty Tile & Grout Cleaner | | | | | |
| Aqua Mix Heavy Duty Tile & Grout Cleaner with olive oil | | | | | |
| Aqua Mix Heavy Duty Stripper & Cleaner | | | | | |
| Aqua Mix Heavy Duty Stripper & Cleaner with olive oil | | | | | |
| Aqua Mix 1 & 2 Deep Clean | | | | | |
| Aqua Mix 1 & 2 Deep Clean with olive oil | | | | | |

Cleaning of equipment

Clean tools and hands with water before material dries.

Storage

Keep from freezing.



Health Precautions

May irritate eyes. May irritate skin. Do not swallow. Do not get in eyes. Do not get on skin or clothing. Do not breathe fumes. KEEP OUT OF REACH OF CHILDREN. Wear safety glasses and chemical-resistant gloves. First Aid Treatment: If swallowed, call a poison control center or doctor immediately. Do not induce vomiting. If in eyes, rinse with water 15 minutes. If on skin, rinse well with water.

Conformance to Building Codes

Installation must comply with the requirements of all applicable local, state and federal code jurisdictions.

6 Availability & Cost

| Item Code | Size | Grout Color | Package | |
|--------------|---------|--------------------|---------|--|
| Part A | | | | |
| LWCEG09A-EA | 1.3 lbs | #9 Natural Gray | Tub | |
| LWCEG10A-EA | 1.3 lbs | #10 Antique White | Tub | |
| LWCEG11A-EA | 1.3 lbs | #11 Snow White | Tub | |
| LWCEG19A-EA | 1.3 lbs | #19 Pewter | Tub | |
| LWCEG22A-EA | 1.3 lbs | #22 Sahara Tan | Tub | |
| LWCEG45A-EA | 1.3 lbs | #45 Summer Wheat | Tub | |
| LWCEG50A-EA | 1.3 lbs | #50 Nutmeg | Tub | |
| LWCEG52A-EA | 1.3 lbs | #52 Tobacco Brown | Tub | |
| LWCEG59A-EA | 1.3 lbs | #59 Saddle Brown | Tub | |
| LWCEG60A-EA | 1.3 lbs | #60 Charcoal | Tub | |
| LWCEG95A-EA | 1.3 lbs | #95 Sable Brown | Tub | |
| LWCEG101A-EA | 1.3 lbs | #101 Quartz | Tub | |
| LWCEG105A-EA | 1.3 lbs | #105 Earth | Tub | |
| LWCEG115A-EA | 1.3 lbs | #115 Platinum | Tub | |
| LWCEG122A-EA | 1.3 lbs | #122 Linen | Tub | |
| LWCEG135A-EA | 1.3 lbs | #135 Mushroom | Tub | |
| LWCEG145A-EA | 1.3 lbs | #145 Light Smoke | Tub | |
| LWCEG156A-EA | 1.3 lbs | #156 Fawn | Tub | |
| LWCEG165A-EA | 1.3 lbs | #165 Delorean Gray | Tub | |
| LWCEG172A-EA | 1.3 lbs | #172 Urban Putty | Tub | |
| LWCEG180A-EA | 1.3 lbs | #180 Sandstone | Tub | |
| LWCEG183A-EA | 1.3 lbs | #183 Chateau | Tub | |
| LWCEG185A-EA | 1.3 lbs | #185 New Taupe | Tub | |
| LWCEG186A-EA | 1.3 lbs | #186 Khaki | Tub | |
| LWCEG333A-EA | 1.3 lbs | #333 Alabaster | Tub | |
| LWCEG335A-EA | 1.3 lbs | #335 Winter Gray | Tub | |
| LWCEG370A-EA | 1.3 lbs | #370 Dove Gray | Tub | |
| LWCEG380A-EA | 1.3 lbs | #380 Haystack | Tub | |
| LWCEG381A-EA | 1.3 lbs | #381 Bright White | Tub | |
| LWCEG382A-EA | 1.3 lbs | #382 Bone | Tub | |
| LWCEG386A-EA | 1.3 lbs | #386 Oyster Gray | Tub | |
| LWCEG401A-EA | 1.3 lbs | #540 Truffle | Tub | |
| LWCEG541A-EA | 1.3 lbs | #541 Walnut | Tub | |
| LWCEG542A-EA | 1.3 lbs | #542 Graystone | Tub | |
| LWCEG543A-EA | 1.3 lbs | #543 Driftwood | Tub | |
| LWCEG544A-EA | 1.3 lbs | #544 Rolling Fog | Tub | |
| LWCEG545A-EA | 1.3 lbs | #545 Bleached Wood | Tub | |
| LWCEG546A-EA | 1.3 lbs | #546 Cape Gray | Tub | |
| LWCEG547A-EA | 1.3 lbs | #547 Ice Blue | Tub | |
| LWCEG548A-EA | 1.3 lbs | #548 Surf Green | Tub | |
| Part B | | | • | |
| LWCEGB1-EA | 9.5 lbs | n/a | Pail | |
| LWCEGB2 | 19 lbs | n/a | Pail | |



See our color card for truest color representation when selecting or specifying a grout color. Final installed shade may vary with the tile type, color and porosity as well as jobsite conditions and finishing techniques. For best results, perform a test on a small, inconspicuous area or create a sample board prior to installation.

7 Product Warranty

Obtain the applicable **LIMITED PRODUCT WARRANTY** at www.custombuildingproducts.com/product-warranty or send a written request to Custom Building Products, Inc., Five Concourse Parkway, Atlanta, GA 30328, USA. Manufactured under the authority of Custom Building Products, Inc. © 2017 Quikrete International, Inc.

When CEG-Lite™ 100% Solids Commercial Epoxy Grout is used as a part of a qualifying full installation system of CUSTOM products in an approved installation environment, the installation can qualify for up to a lifetime system warranty. CUSTOM will repair and/or replace, at its discretion, the affected area of the system. For more information, find details and limitations to this warranty at custombuildingproducts.com.

For commercial kitchen and industrial applications, contact your Custom Building Products representative for details regarding warranty durations.

8 Product Maintenance

Clean with a neutral cleaner such as <u>Aqua Mix Concentrated Stone & Tile Cleaner</u> or <u>TileLab Grout & Tile Cleaner</u>.

9 Technical Services Information

For technical assistance, contact Custom technical services at 800-282-8786 or visit <u>custombuildingproducts.com</u>.

10 Filing System

Additional product information is available from the manufacturer upon request.

Related Products

Commercial 100% Silicone Sealant



Coverage

Per unit CEG-Lite combined 1 Part A + 1 Part B (9.5 lb. / 4.3 kg) in ft² (m²).

Coverage for larger size CEG-Lite (19 lb. / 8.6 kg) is double the values below.

| Tile Size Width x Length x Thickness | Joint Width | | | | | | |
|---|--|---|---|---|---|---|--|
| | 1/16" (1.6 mm) | 1/8" (3 mm) | 3/16" (4.8 mm) | 1/4" (6.3 mm) | 3/8" (9.5 mm) | 1/2" (13 mm) | |
| 1" x 1" x 1/4" (2.5 x 2.5 x .64 cm) | 52 ft² (4.8 m²) | 29 ft² (2.7 m²) | 21 ft² (2 m²) | 18 ft² (1.7 m²) | 14 ft² (1.3 m²) | 13 ft² (1.2 m²) | |
| 2" x 2" x 1/4" (5 x 5 x .64 cm) | 97 ft² (9 m²) | 52 ft² (4.8 m²) | 36 ft² (3.4 m²) | 29 ft² (2.7 m²) | 21 ft² (2 m²) | 18 ft² (1.7 m²) | |
| 3" x 3" x 1/4" (7.6 x 7.6 x .64 cm) | 143 ft ² (13.3 m ²) | 74 ft² (6.9 m²) | 52 ft² (4.8 m²) | 40 ft ² (3.7 m ²) | 29 ft² (2.7 m²) | 23 ft² (2.2 m²) | |
| 4.25" x 4.25" x 1/4" (10.8 x 10.8 x .64 cm) | 200 ft ² (18.6 m ²) | 103 ft ² (9.6 m ²) | 71 ft² (6.6 m²) | 54 ft ² (5.1 m ²) | 38 ft ² (3.6 m ²) | 30 ft ² (2.8 m ²) | |
| 4" x 8" x 1/2" (10.2 x 20.3 x 1.3 cm) | 125 ft² (11.6 m²) | 64 ft ² (5.9 m ²) | 44 ft² (4.1 m²) | 33 ft² (3.1 m²) | 23 ft² (2.1 m²) | 18 ft² (1.7 m²) | |
| 6" x 6" x 1/4" (15.2 x 15.2 x .64 cm) | 280 ft ² (26 m ²) | 143 ft ² (13.3 m ²) | 97 ft² (9 m²) | 74 ft² (6.9 m²) | 52 ft² (4.8 m²) | 40 ft ² (3.7 m ²) | |
| 6" x 6" x 1/2" (15.2 x 15.2 x 1.3 cm) | 140 ft² (13 m²) | 71 ft² (6.6 m²) | 49 ft² (4.6 m²) | 37 ft² (3.4 m²) | 26 ft² (2.4 m²) | 20 ft ² (1.9 m ²) | |
| 8" x 8" x 3/8" (20.3 x 20.3 x 1 cm) | 248 ft ² (23 m ²) | 126 ft ² (11.7 m ²) | 85 ft ² (7.9 m ²) | 65 ft² (6 m²) | 45 ft² (4.2 m²) | 34 ft² (3.2 m²) | |
| 12" x 12" x 3/8" (30.5 x 30.5 x 1 cm) | 369 ft ² (34.3 m ²) | 187 ft ² (17.3 m ²) | 126 ft ² (11.7 m ²) | 95 ft² (8.8 m²) | 65 ft² (6 m²) | 50 ft ² (4.6 m ²) | |
| 16" x 16" x 3/8" (40.6 x 40.6 x 1 cm) | 491 ft ² (45.6 m ²) | 248 ft² (23 m²) | 166 ft ² (15.4 m ²) | 126 ft² (11.7 m²) | 85 ft² (7.9 m²) | 65 ft² (6 m²) | |
| 18" x 18" x 3/8" (45.7 x 45.7 x 1 cm) | 552 ft ² (51.3 m ²) | 278 ft ² (25.8 m ²) | 187 ft ² (17.3 m ²) | 141 ft ² (13.1 m ²) | 95 ft² (8.8 m²) | 72 ft² (6.7 m²) | |
| 20" x 20" x 3/8" (50.8 x 50.8 x 1 cm) | 613 ft ² (56.9 m ²) | 309 ft² (28.7 m²) | 207 ft ² (19.2 m ²) | 156 ft ² (14.5 m ²) | 105 ft² (9.8 m²) | 80 ft ² (7.4 m ²) | |
| 24" x 24" x 3/8" (61 x 61 x 1 cm) | 735 ft² (68.3 m²) | 369 ft ² (34.3 m ²) | 248 ft ² (23 m ²) | 187 ft ² (17.4 m ²) | 126 ft ² (11.7 m ²) | 95 ft² (8.8 m²) | |
| 6" x 24" x 3/8" (15.2 x 61 x 1 cm) | 296 ft ² (27.5 m ²) | 150 ft ² (13.9 m ²) | 101 ft ² (9.4 m ²) | 77 ft² (7.1 m²) | 53 ft² (4.9 m²) | 40 ft ² (3.8 m ²) | |
| 12" x 24" x 3/8" (30.5 x 61 x 1 cm) | 491 ft ² (45.6 m ²) | 248 ft ² (23 m ²) | 166 ft ² (15.5 m ²) | 126 ft ² (11.7 m ²) | 85 ft² (7.9 m²) | 65 ft² (6 m²) | |
| 6" x 36" x 3/8" (15.2 x 91.4 x 1 cm) | 317 ft ² (29.4 m ²) | 161 ft² (15 m²) | 108 ft² (10 m²) | 82 ft² (7.6 m²) | 56 ft² (5.2 m²) | 43 ft² (4 m²) | |
| 9 x 36" x 3/8" (22.9 x 91.4 x 1 cm) | 443 ft ² (41.2 m ²) | 223 ft² (20.7 m²) | 150 ft ² (13.9 m ²) | 114 ft² (10.6 m²) | 77 ft² (7.2 m²) | 59 ft² (5.5 m²) | |
| 12" x 48" x 3/8" (30.5 x 122 x 1 cm) | 589 ft² (54.7 m²) | 296 ft² (27.5 m²) | 199 ft² (18.5 m²) | 150 ft ² (13.9 m ²) | 101 ft² (9.4 m²) | 77 ft² (7.2 m²) | |

Chart for estimating purposes. Coverage may vary based on installation practices and jobsite conditions. For more tile and joint sizes, use the <u>Material Calculator</u> at CustomBuildingProducts.com or contact CUSTOM Technical Services at <u>800-282-8786</u>.

