

# CL-XP1

## 1 Product Name

CL-XP1

## 2 Manufacturer

Custom Building Products  
 Technical Services  
 10400 Pioneer Boulevard, Unit 3  
 Santa Fe Springs, CA 90670  
 Customer Support: 800-272-8786  
 Technical Services: 800-282-8786  
 Fax: 800- 200-7765  
 Email: [contactus@cbpmail.net](mailto:contactus@cbpmail.net)  
[custombuildingproducts.com](http://custombuildingproducts.com)

## 3 Product Description

**This product has been discontinued. Please reference our [CustomTech line](#) of products.**

CL-XP1™ is a high strength, low prep self-leveling underlayment that levels floors prior to the installation of ceramic tile, natural stone tile, resilient flooring, carpet, wood and other floor coverings. This quick-setting underlayment can be applied to 2" (5 cm) thick in one pour and seeks its own level in minutes. Formulated to have high compressive strength and abrasion resistance, CL-XP1 achieves an extra heavy rating for high impact use in food plants, hospitals, and kitchens. CL-XP1 may be applied to in residential structures with floor joists up to 24" (61 cm) o.c. Formulated using Controlled Cure Technology,™ CL-XP1 helps eliminate installation problems such as bond failure, crumbling and staining of resilient flooring caused by the free moisture found in traditional underlayments.

### Key Features

- Low prep formula - sweep, prime and pour
- Superior resistance to cracking from shrinkage
- 5,000 PSI compressive strength
- Exceeds ASTM requirements for resilient floor covering installations
- Levels floors from feather edge to 2" thick

### Uses

#### Suitable as an Underlayment for:

- Carpet
- Wood, parquet
- Vinyl composition tile (VCT)
- Sheet vinyl flooring
- Laminated flooring
- Vitreous, semi-vitreous or non-vitreous tile
- Ceramic, mosaic, quarry or cement body tile
- Impervious porcelain and glass tile
- Brick and stone veneer
- Cement-based precast terrazzo
- Natural stone tile
- Stone, terrazzo



### Suitable Substrates

- Absorbent concrete
- Non-absorbent concrete
- Lightweight concrete
- Gypsum-based underlayments
- Existing ceramic tile
- Cement terrazzo
- Epoxy terrazzo
- Exterior grade plywood
- OSB
- Cutback adhesive residue
- Resilient flooring
- Properly prepared steel and aluminum

### Composition of Product

CL-XP1 is a dry, proprietary blend of co-polymers, cements and inorganic chemicals.

### Benefits of Product in the Installation

- No shotblasting required on acceptable surfaces
- Abrasion-resistant; holds up to traffic during construction
- Can be applied from featheredge to 2" (5 cm) thick in a single pour
- Reduces bond failure and crumbling of resilient flooring
- Cures fast and develops high early-strength for quick installation
- Rated for extra heavy use on concrete and wood subfloors with joists to 24" (61 cm) per ASTM C627.

### Limitations to the Product

- For interior use only.
- Do not bond directly to hardwood, Luan plywood, particle board, parquet, cushion or sponge-back vinyl flooring, metal, fiberglass or plastic. Contact technical services for recommendations.
- Do not use as a permanent wear surface.
- Do not use on sloped surfaces that require drainage.
- Precautions should be taken when applying over post-tensioned concrete, pre-stressed concrete or prefabricated concrete planks. Contact technical services for further details.



# CL-XP1

## Packaging

50 lb (22.68 kg) Bags

## 4 Technical Data

### Applicable Standards

ASTM International (ASTM)

- ASTM C1708 Standard Test Methods for Self-leveling Mortars Containing Hydraulic Cements
- ASTM C627 Standard Test Method for Evaluating Ceramic Floor Tile Installation Systems Using the Robinson-Type Floor Tester
- ASTM F1869 Standard Test Method for Measuring Moisture Vapor
- ASTM F710 Standard Practice for Preparing Concrete Floors to Receive Resilient Flooring

Resilient Floor Covering Institute (RFCI) Recommended Work Practices for Removal of Resilient Floor Coverings

Tile Council of North America (TCNA) TCNA Handbook for Ceramic Tile Installation, TCNA Method EJ171

American National Standards Institute (ANSI) ANSI A108.01 and A108.02 of the American National Standards for the Installation of Ceramic Tile

### Technical Chart

Property	Test Method	Typical Results
Pot Life		15 minutes
Flow Time		18 minutes
Compressive Strength	ASTM C-109	5,000 psi
Flexural Strength	ASTM C-109	1,100 psi (7.58 MPa)
Walkable Hardness		2 - 4 Hours
Time Before Installing Floor Covering		
Ceramic Tile		> 4 Hours
Other Floor Covering		> 16 Hours
Robinson Test	ASTM C-627	Extra Heavy
Installed Density - Dry		approx. 118 lbs/cu ft

### Environmental Consideration

Custom Building Products is committed to environmental responsibility in both products produced and in manufacturing practices. Use of this product can contribute to LEED® certification

## 5 Instructions

### General Surface Prep

**USE CHEMICAL-RESISTANT GLOVES, such as nitrile, when handling product.**

All surfaces must be structurally sound, clean, dry and free from contaminants that would prevent a good bond. Concrete must be fully cured. Refer to final flooring manufacturer's requirements for maximum moisture vapor transmission limitations. Concrete surfaces **should be primed with an appropriate Custom® primer**. Smooth concrete surfaces, existing glazed tile, terrazzo, or polished stone may need to be roughened or scarified and treated with an appropriate **Custom® primer**. For increased performance in demanding applications, concrete surfaces can be mechanically profiled and prepared by shotblasting, sandblasting, water-jetting, scarifying, diamond-grinding or other engineered approved methods (reference ICRI CSP 3 standards for acceptable profile height).

### Bonding to Concrete Surfaces

Contaminants or curing compounds should be mechanically removed before installation. Concrete must be free of efflorescence and not subject to moisture beyond the floor covering manufacturers' limits or hydrostatic pressure. Lightweight concrete surfaces must have a **tensile strength in excess of 200 psi (1.4 n/mm<sup>2</sup>)**.

### Bonding to Plywood Surfaces

Plywood floors, including those under resilient flooring, must be structurally sound and must meet all industry guidelines. For questions about proper subfloor installation, call Custom Technical Services. A **2.5 lb/yd<sup>2</sup> metal lath must be fastened every 6" - 8" (15 - 20 cm) with fasteners that have a galvanized or corrosion-resistant coating over primed surfaces.**

### OSB Underlayments

OSB underlayments should be coated with 10-15 mils of [RedGard® Waterproofing and Crack Prevention Membrane](#) prior to priming with an appropriate [Custom® primer](#). A **2.5 lb/yd<sup>2</sup> metal lath must be fastened every 6" - 8" (15 - 20 cm) with fasteners that have a galvanized or corrosion-resistant coating. A minimum of 1/4" (6 mm) of CL-XP1 can be applied over this properly prepared OSB.**

### Bonding to Gypsum Surfaces

Gypsum-based underlayments must obtain a minimum 2000 psi (13.8 MP) compressive strength. The underlayment must be sufficiently dry **and properly cured to the manufacturer's specifications for permanent, non-moisture permeable coverings**. Surfaces must be structurally sound and subject to deflection not to exceed the current industry standards. Surfaces shall be free of all grease, oil, dirt, dust, curing compounds, waxes, sealers, efflorescence, or any other foreign matter.



# CUSTOM®

# CL-XP1

All Gypsum surfaces should be primed with a properly applied sealer or a primer coat of [RedGard](#), consisting of 1 part RedGard diluted with 4 parts clean, cool water. Mix in a clean bucket at low speed to obtain a lump-free solution. The membrane can be brushed, rolled or sprayed to achieve an even coat. Apply the waterproofing coat to the floor at a rate of 300 sq. ft./l (7.5 sq. m/L). Drying time depends on site conditions, but is normally less than 1 hour. Extremely porous surfaces may require 2 coats. At this point, an appropriate [Custom® primer](#) and CL-XP1 can be applied to the primed lightweight or gypsum based surface. Refer to the individual product data sheet or packaging directions for application instructions. Expansion joints must be installed in accordance with local building codes and industry guidelines.

## Bonding to Cutback Adhesive

Adhesive layers must be removed. **Use extreme caution;** adhesives may contain asbestos fibers. Do not sand or grind adhesive residue, as harmful dust may result. Never use adhesive removers or solvents, as they soften the adhesive and may cause it to penetrate into the concrete. Adhesive residue must be wet-scraped to the finished surface of the concrete, leaving only the transparent staining from the glue. To determine desirable results, do a test bond area before starting. Refer to the RFI Pamphlet "Recommended Work Practices for Removal of Resilient Floor Coverings" for further information.

## Priming

Prime all surfaces with an appropriate Custom® primer before application.

## Joints or Cracks in Substrate

Expansion joints and cold joints, as described in ANSI A108.01, should be carried from the substrate up through the tile or flooring surface and filled with an appropriate elastomeric sealant, such as Custom's® 100% Silicone Caulk. For the proper treatment of control or saw cut joints and cracks for flooring, refer to ASTM F710. For tile installations, refer to TCNA Details EJ171, F125, & F125A. Contact Custom's® technical services for additional information.

## Mixing Ratios

Mix the entire 50 lb (22.68 kg) bag of powder with 5.0 - 5.5 quarts (4.7 - 5.2 L) of clean, cool water.

## Mixing Procedures

### Barrel:

Mix 50 lb. (22.68 kg) bag of powder with an appropriate amount of clean, cool water. Slowly add powder to water while mixing with a heavy-duty 1/2" (13 mm) electric drill and an "egg-beater" mixing paddle at 800 - 1200 RPM. Thoroughly mix for 2 minutes to a lump-free consistency. Do not overmix. Overmixing or moving the mixer up and down during the mixing process could trap air, which could shorten the pot life or cause pinholing during application and curing.

### Pumping:

CL-XP1 can be pumped with an appropriate mixing pump. Adjust the water setting to obtain the optimum workability. Do NOT overwater.

## Application of Product

Apply an appropriate Custom® primer according to the specifications in the respective technical data sheet for each product. Pour or pump CL-XP1, then spread with a long-handled gauged spreader. Will flow during the first 20 minutes. For featheredging and touch-ups, use a smoothing tool. Can be applied up to 2" (5 cm) thick in one application. If a second layer is required, install immediately after the first layer has set to a walkable hardness. If the first layer has dried over 12 hours, re-prime before second application. Dries to a walkable hardness in 2 - 4 hours. For pumping and large scale applications, contact Custom's Technical Services Department for more information.

## Curing of Product

Install non-moisture-sensitive ceramic tile or stone in 4 hours; most floor coverings can be installed after 16 hours. Drying time can vary with temperature and humidity. Test for moisture content before applying vinyl or wood flooring to the surface of the self-leveler.

## Cleaning of equipment

Clean with water before material dries.

## Health Precautions

This product contains Portland cement. Avoid eye contact or prolonged contact with skin. Wash thoroughly after handling. If eye contact occurs, flush with water for 15 minutes and consult a physician. Use with adequate ventilation; do not breathe dust and wear a NIOSH approved respirator. If ingested, do not induce vomiting; call a physician immediately.

## Conformance to Building Codes

Installation must comply with the requirements of all applicable local, state and federal code jurisdictions.

## 6 Availability & Cost

LOCATION	ITEM CODE	SIZE	PACKAGE
USA/Canada	CLXP150	50 lb (22.68 kg)	Bag

## 7 Product Warranty

Custom® Building Products warrants to the original consumer purchaser that its product shall be free from defects in material and workmanship under normal and proper usage for a period of one year following the date of original purchase. Custom's® sole liability under this warranty shall be limited to the replacement of the product. Some states, countries or territories do not allow the exclusion or limitation of incidental or consequential damages, so the above limitation or exclusion may not apply to you. This warranty will not extend to any product which has been modified in any way or which has not been used in accordance with Custom's® printed instructions. Custom® makes no other warranties either expressed or implied. This warranty gives you specific legal rights, and you may have other rights that vary from state to state or from one country/territory to another. This warranty is not transferrable.

## 8 Product Maintenance

Properly installed product requires no special maintenance.



# CL-XP1

---

## 9 Technical Services Information

For technical assistance, contact Custom technical services at 800-272-8786 or visit [custombuildingproducts.com](http://custombuildingproducts.com).

## 10 Filing System

Additional product information is available from the manufacturer upon request.

# CL-XP1

---

**Coverage**

SQUARE FOOT COVERAGE PER 50 LB BAG (SQUARE METER PER 22.68 KG)

Thickness	Min Coverage	Max Coverage
1/8" (3.18 mm)	47 ft <sup>2</sup> (4.36 M <sup>2</sup> )	51 ft <sup>2</sup> (4.73 M <sup>2</sup> )
1/4" (6.35 mm)	23.5 ft <sup>2</sup> (2.18 M <sup>2</sup> )	25.5 ft <sup>2</sup> (2.36 M <sup>2</sup> )
1/2" (12.7 mm)	11.75 ft <sup>2</sup> (1.09 M <sup>2</sup> )	12.75 ft <sup>2</sup> (1.18 M <sup>2</sup> )
1" (25.4 mm)	5.87 ft <sup>2</sup> (0.54 M <sup>2</sup> )	6.37 ft <sup>2</sup> (0.59 M <sup>2</sup> )
1.5" (38.1 mm)	4.4 ft <sup>2</sup> (0.4 M <sup>2</sup> )	4.78 ft <sup>2</sup> (0.44 M <sup>2</sup> )
2" (50.8 mm)	2.93 ft <sup>2</sup> (0.27 M <sup>2</sup> )	3.18 ft <sup>2</sup> (0.29 M <sup>2</sup> )

**CUSTOM<sup>®</sup>**