


LevelQuik® ES (Extended Setting) Self-Leveling Underlayment



1. Product Name

LevelQuik® ES (Extended Setting) Self-Leveling Underlayment

2. Product Description

LevelQuik® ES is a premium, calcium aluminate based, high quality self-leveling underlayment that levels floors prior to the installation of ceramic tile, natural stone tile, resilient flooring, carpet, wood, and other floor coverings. Formulated for extended set and with Controlled Cure Technology™, it helps eliminate installation problems such as bond failure, crumbling, and staining of resilient flooring caused by the free moisture found in a traditional underlayment.

Key Features

- Easy to mix and place with extended set
- High flow formula with excellent handling and exceptional flow retention properties
- Levels from feather edge to 1.5" in one pour
- Over 4000 psi compressive strength at 28 days
- Formulated to reduce shrinkage and minimize crack formation
- Exceeds ASTM requirements for resilient floor covering installations

Uses

Suitable as an Underlayment for:

- Carpet
- Wood and parquet flooring
- Luxury Vinyl Tile/Planks (LVT/LVP)
- Vinyl composition flooring (VCT)
- Sheet vinyl and rubber flooring
- Laminated flooring
- Ceramic, mosaic, quarry or cement body tile
- Impervious porcelain and glass tile
- Cement-based precast terrazzo
- Natural stone tile
- Terrazzo

Suitable Substrates

- Absorbent and non-absorbent concrete
- Lightweight concrete
- Gypsum-based underlayment
- Existing ceramic tile
- Cement and epoxy terrazzo
- Exterior grade plywood and OSB
- Cutback adhesive residue

- Well adhered resilient flooring
- Properly prepared steel and aluminum

Composition of Product

LevelQuik® is a proprietary dry blend of copolymers, cements and inorganic chemicals.

Benefits of Product in the Installation

- No shot blasting required on acceptable surfaces
- Can be applied from featheredge to 1.5" (3.8 cm) thick in a single pour
- Reduces bond failure and crumbling of resilient flooring
- Cures fast and develops high early-strength for quick installation
- Rated for extra heavy use on concrete and wood subfloors with joists to 24" (61 cm) per ASTM C627

Limitations to the Product

- For use in interior dry areas. Ambient, substrate and product temperature is to be between 50° F (10° C) 90° F (32° C). Chill or warm water when needed to make mixture fall between these temperatures.
- Assure that substrates are not wet from condensation in ambient conditions of high humidity. High humidity conditions may affect surface drying and subsequently final results.
- Do not bond directly to hardwood, Luan plywood, particle board, parquet, cushion or sponge-back vinyl flooring, metal, fiberglass or plastic. Contact technical services for recommendations.
- Do not use as a permanent wear surface.
- Do not use on sloped surfaces that require drainage.
- Precautions for finished flooring deflection and movement joint requirements should be considered when applying over post-tensioned concrete, pre-stressed concrete or prefabricated concrete planks. Contact technical services for further details.

Packaging

50 lb (22.68 kg) Bags

3. Technical Data

Applicable Standards

ASTM International (ASTM)

- ASTM C1708 Standard Test Methods for Self-leveling Mortars Containing Hydraulic Cements
- ASTM F2873 Standard Practice for the Installation of Self-Leveling Underlayment and the Preparation of Surface to Receive Resilient Flooring
- ASTM C627 Standard Test Method for Evaluating Ceramic Floor Tile Installation Systems Using the Robinson-Type Floor Tester
- ASTM F2170 Standard Test Method for Determining Relative Humidity in Concrete Floor Slabs Using in situ Probes
- ASTM F1869 Standard Test Method for Measuring Moisture Vapor
- ASTM F710 Standard Practice for Preparing Concrete Floors to Receive Resilient Flooring

LevelQuik® ES (Extended Setting) Self-Leveling Underlayment

Resilient Floor Covering Institute (RFCI) Recommended Work Practices for Removal of Resilient Floor Coverings

Tile Council of North America (TCNA) TCNA Handbook for Ceramic Tile Installation, TCNA Method EJ171

American National Standards Institute (ANSI) ANSI A108.01 and A108.02 of the American National Standards for the Installation of Ceramic Tile

Technical Chart

Property	Test Method	Typical Results @70°F (21°C) and 50%RH
Pot Life (in bucket)		>15 minutes
Healing Time (Re-heal)	ASTM C-1708	>18 minutes
Compressive Strength at 28 days	ASTM C-1708	>4,300 psi
Flexural Strength at 28 days	ASTM C-348	>800 psi (5.5 MPa)
Walkable Hardness		12 Hours
Installed Density - Dry		105.0-112.0 lb/ft ³
Robinson Test	ASTM C-627	Extra Heavy
Time Before Installing Floor Covering		
Ceramic tile/Non-moisture sensitive floor covering		18-24 Hours
Moisture-sensitive floor coverings		>30Hours

Environmental Consideration

Custom® Building Products is committed to environmental responsibility in both products produced and in manufacturing practices. Use of this product can contribute towards LEED® v3 certification:

- Up to 2 points towards MR Credit 5, Regional Materials

4. Instructions

General Surface Prep

USE CHEMICAL-RESISTANT GLOVES, such as nitrile, when handling product.

All surfaces must be structurally sound, clean, dry and free from contaminants such as grease, oil, dirt, dust, curing compounds, waxes, sealers, efflorescence, or any other foreign matter. Concrete must be fully cured and absorb water. Smooth concrete surfaces, existing glazed tile, terrazzo, or polished stone may need to be roughened or scarified. Refer to [LevelQuik® Advanced Acrylic Primer](#) technical datasheet for use in lieu of mechanical preparation or when applying over [Custom TechMVC™ Moisture Vapor and Alkalinity Barrier](#). For increased performance in demanding applications, concrete surfaces can be mechanically profiled and prepared by shotblasting, sandblasting, scarifying, diamond-grinding or other engineered approved methods (reference ICRI CSP 3 standards for ideal profile height). Any existing flooring must be well bonded and stripped of old finish.

CUSTOM® products may be used in assemblies over concrete with high moisture vapor emission levels provided that other materials such as finish flooring, adhesives or membranes are approved in these conditions. Consult the manufacturers for their limitations and requirements. Additionally, any sources of moisture are to be limited to initial concrete placement and not from sources such as water intrusion or from a lack of an effective vapor retarder/barrier.

Assembly mockups will determine suitability for these conditions on

specific projects. Contact CUSTOM Technical Services for product information (800) 282-8786

Bonding To Concrete Surfaces

In addition to general surface preparation requirements listed above, concrete must be free of efflorescence and hydrostatic pressure. Concrete surfaces must have a tensile strength in excess of 200 psi (1.4 n/mm²). Concrete that was treated with curing compounds must be evaluated for suitability or mechanically removed.

Bonding to Gypsum Surfaces

Bonding to Gypsum Surfaces Gypsum-based underlayment must be solid and structurally sound, achieving a compressive strength >2000psi (13.8 MP) Remove any unacceptable surfaces. The underlayment must be sufficiently dry and properly cured to the manufacturer's specifications for permanent, non-moisture permeable coverings. Substrate deflection not to exceed the current industry standards. All Gypsum surfaces are required to be sealed or primed prior to leveling. Apply [LevelQuik® Advanced Acrylic Primer](#) directly to the gypsum or over gypsum manufacturer's sealer. Dilute TechPrime A 3-parts water to 1-part primer with clean, potable water. Apply a second application of primer diluted 1:1. Drying time depends on site conditions, but is normally less than 1 hour between coats. Leveler can be applied to the primed surface after primer dries. Gypsum based underlayment used in tile or stone applications may require waterproofing or crack isolation. For these applications we recommend applying [RedGard® Waterproofing and Crack Prevention Membrane](#) over leveler once cured.

Bonding to Plywood and OSB Surfaces

Bonding to Plywood and OSB Surfaces Plywood and OSB including those under resilient flooring, must be structurally sound and must meet all industry guidelines. Subfloors shall be structurally compliant to building codes and area usage including joist blocking or bracing, be sound, clean, dry, and free from contaminants that would prevent adhesion. Any loose plywood or deflecting areas must be addressed prior to leveler installation. Floors may be prepared by sanding. Do not use sweeping compounds, or chemicals or solvents to clean the floor. Fasten 2.5 lb./yd² metal lath every 6" → 8" (15 → 20 cm) with fasteners that have a galvanized or corrosion-resistant coating over primed surfaces. It is generally accepted that wood-framed substrate deflection for Porcelain tiles is limited to <L/360; natural stone <L/720. Dimensionally weaker finishes such as natural stone, Saltillo, cement, glass tile and resilient flooring installations may require additional plywood layers based on area size/span; deflection; leveler thickness and project usage, live and dead loads. Leveler may require ½" thickness to replace cement backerboard use under tile or to provide adequate rigidity for floor covering. To help prevent failures from substrate creep install heavy dead loads such as stone countertops prior to leveler and tile or flooring installation. Refer to ANSI A108 AN2 General Requirements for Subsurbaces and TCNA details for further information for tile installations or contact CUSTOM Technical Services. Block any open spaces to prevent leveler spilling to adjoining areas. Fill joints with a CUSTOM patching compound such as SpeedFinish™ Patching & Finishing Compound All wood subfloors require a primer application of undiluted LevelQuik® Advanced Acrylic Primer or MBP - Multi-Surface Bonding Primer.

Bonding to Cutback Adhesive

Adhesive layers must be removed. Use extreme caution; adhesives may contain asbestos fibers. Do not sand or grind adhesive residue, as harmful dust may result. Never use adhesive removers or solvents, as they soften the adhesive and may cause it to penetrate into the concrete. Adhesive residue must be wet-scraped to the finished surface of the concrete, leaving only the transparent staining from the glue. To determine desirable results, do a test bond area before starting. Refer to the RFCI Pamphlet

LevelQuik® ES (Extended Setting) Self-Leveling Underlayment

"Recommended Work Practices for Removal of Resilient Floor Coverings" for further information.

Priming

Prime all surfaces with an appropriate Custom® primer before application of LevelQuik ES. Refer to [LevelQuik® Advanced Acrylic Primer](#), or [TechPrime™ E 100%-Solids Epoxy Primer](#) technical datasheets.

Movement Joint Placement Joints or Cracks in Substrate


Expansion joints and cold joints, as described in ANSI A108.01, should be carried from the substrate up through the tile or flooring surface and filled with an appropriate elastomeric sealant, such as Custom's® [Commercial 100% Silicone Sealant](#). For the proper treatment of control or saw cut joints and cracks for flooring, refer to ASTM F710. For tile installations, refer to TCNA Details EJ171, F125 & F125A. Contact Custom Technical Services for additional information.

Mixing Ratios

Mix the entire 50 lb. (22.68 kg) bag of powder with 5.25 - 5.75 quarts (5 - 5.4 L) of clean, cool water.

Mixing Procedures

Barrel:

Mix 50 lb. (22.68 kg) bag of powder with the appropriate amount of clean, cool water. Slowly add powder to water while mixing with a heavy-duty 1/2" (13 mm) electric drill and an  mixing paddle at minimum 650 RPM. Thoroughly mix for 2 minutes to a lump-free consistency. Do not overmix. Overmixing or moving the mixer up and down during the mixing process could trap air, which could shorten the pot life or cause pin holing during application and curing.

Pumping:

LevelQuik ES can be pumped with a mixing pump. Adjust the water setting to obtain the optimum workability. Do NOT overwater. Pump the mix and use spreader to evenly distribute the materials to desired thickness.

Application of Product

Pour the mixed product and spread with a long-handled gauge rake to the desired thickness. Directly after the topping has been dispersed, use a smoothing blade to break the material's surface rheology and blend any inconsistencies to create a more uniform or homogeneous appearance. Keep a wet edge when pouring multiple mixes in the same area.

If a second layer is required, install immediately after the first layer has set to a walkable hardness. If the first layer has dried over 12 hours, re-prime before second application.

*** Always install a test area to confirm proper bonding as well as a desired appearance.

IMPORTANT NOTES: Self leveling cement based products may exhibit slight cracking due to structure and substrate moment; shrinkage; and creep. Sharp or reentrant wall corners can contribute to crack formation. These cracks are considered normal. Other causes of cracking are due to high ambient or substrate temperatures; wind or air flow; water ratios and mixing technique. When surface is sealed with clear or semi-transparent coatings, these cracks may become more visible.

Curing of Product

Install non-moisture-sensitive ceramic tile or stone in 12 hours; most floor coverings can be installed after 30 hours. Drying time can vary with temperature and humidity. Confirm moisture limitations of flooring and adhesives before installing over leveler.

Cleaning of Equipment

Clean with water before the material dries.

Health Precautions

This product contains Portland cement. Avoid eye contact or prolonged contact with skin. Wash thoroughly after handling. If eye contact occurs, flush with water for 15 minutes and consult a physician. Use with adequate ventilation; do not breathe dust and wear a NIOSH-approved respirator. If ingested, do not induce vomiting; seek medical attention immediately.

Conformance to Building Codes

Installation must comply with the requirements of all applicable local, state and federal code jurisdictions.

5. Size & Availability

Location	Item Code	Size	Package
USA	LQESL50	50 lb (22.68 kg)	Bag
Canada	CLQESL50	50 lb (22.68 kg)	Bag

6. Product Maintenance

Properly installed product requires no special maintenance. LevelQuik® ES is not recommended as a finish or wear surface.

7. Technical Services Information

For technical assistance, contact Custom® Building Products.

8. Filing System

Additional product information is available from the manufacturer upon request.

Related Products

LevelQuik® Primer

LevelQuik® ES (Extended Setting) Self-Leveling Underlayment

Coverage Chart

TYPICAL SQUARE FOOT COVERAGE PER 50 LB BAG (SQUARE METER PER 22.68 KG)

THICKNESS	COVERAGE
1/8" (3.18 mm)	46 - 48 ft ² (4.2 - 4.4 M ²)
1/4" (6.35 mm)	23 - 24 ft ² (2.1 - 2.2 M ²)
1/2" (12.7 mm)	11.5 - 12 ft ² (1.05 - 1.1 M ²)
1" (25.4 mm)	5.75 - 6 ft ² (0.52 - 0.55 M ²)
1.5" (38.1 mm)	3.8 - 4 ft ² (0.35 - 0.37 M ²)

Chart for estimating purposes. Coverage may vary based on installation practices and jobsite conditions. For more sizes, use the material calculator at CustomBuildingProducts.com or contact CUSTOM Technical Services at 800-282-8786.