CEG-IG

Industrial Grade 100% Solids Epoxy Grout

CUSTOM's Breakthrough In High Performance Epoxy Grouts



- Formulated to stand up to the harshest environments including commercial kitchens and food processing facilities
- Exceeds performance characteristics of ANSI A118.3
- Resistant to thermal shock
- High stain resistance
- Fast curing
- Contains recycled LEED® contributing materials






CEG-IG™ Offers Easy Workability

- Smooth, easy spread formula
- Non-sag properties allow for wall application
- Packs tightly to provide full joints
- No shrinkage
- Water cleanable
- Fast return to service 7 hour cure time at 75°F (23°C)



FULL JOINTS: Lightweight formula packs tightly.



NON-SAG: Grout stays where you put it.



EASY CLEAN-UP: Cleans easily and quickly.

CEG Color Palette

Patent Pending System

CEG-IG and CEG-Lite use the same Part A — 40 Colors Available





CEG Family

	CEG-Lite™	CEG-IG™
Easy to work with Epoxy	-	-
Stain Resistant	-	-
High Moisture Resistance	-	-
Fast Curing	-	-
Water Cleanable	-	-
Exceeds ANSI 118.3	-	-
Available in 40 colors	-	-
Superior Harsh Chemicals Resistance		-
Superior Heat Resistance		-

CEG-IG**



2 Part A + 1 Part B (1 UNIT)

	ITEM CODE	SIZE	PACKAGE
PART A (color)	LWCEGXXXA-EA	1.3 Lbs. (.58 kg)	Tub
PART B (base)	CEGIGB2	27.7 Lbs. (12.5 kg)	Pail

Can be mixed with CEG-PART A or CEG-Lite Part A

SQUARE FOOT COVERAGE PER UNIT						
TILE SIZE	JOINT WIDTH					
IILE SIZE	1/16"	1/8"	3/16"	1/4"	3/8"	1/2"
1" x 1" x 1/4"	103	58	43	36	29	26
2" x 2" x 1/4"	194	103	73	58	43	36
3" x 3" x 1/4"	286	149	103	80	58	47
4 1/4" x 4 1/4" x 1/4"	400	206	141	109	77	61
6" x 6" x 1/4"	560	286	194	149	103	80
8" x 8" x 3/8"	495	251	170	130	89	69
12" x 12" x 3/8"	739	373	251	191	130	99
16" x 16" x 3/8"	983	495	333	251	170	130
18" x 18" x 3/8"	1104	556	373	282	191	145
20" x 20" x 3/8"	1226	617	414	312	211	160
24" x 24" x 3/8"	1470	739	495	373	251	191
6" x 24" x 3/8"	593	300	203	154	105	81
12" x 24" x 3/8"	983	495	333	251	170	130
6" x 36" x 3/8"	634	321	217	164	112	86
9" x 36" x 3/8"	885	446	300	227	154	117
12" x 48" x 3/8"	1178	593	398	300	203	154

CEG-Lite[™]





1 Part A + 1 Part B (9.7 lbs. (4.4 kg)) 2 Part A + 1 Part B (19.4 lbs. (8.8 kg))

	ITEM CODE	SIZE	PACKAGE
PART A (color)	LWCEGXXXA-EA	1.3 Lbs. (.58 kg)	Tub
PART B (base)	LWCEGB1-EA	9.7 lbs. (4.4 kg)	Pail
PART B (base)	LWCEGB2	19.4 lbs. (8.8 kg)	Pail

Can be mixed with CEG-PART A or CEG-Lite Part A

TILE SIZE		JOINT WIDTH					
TILE SIZE	1/16"	1/8"	3/16"	1/4"	3/8"	1/2"	
1" x 1" x 1/4"	52	29	21	18	14	13	
2" x 2" x 1/4"	97	52	36	29	21	18	
3" x 3" x 1/4"	143	74	52	40	29	23	
4 1/4" x 4 1/4" x 1/4"	200	103	71	54	38	30	
6" x 6" x 1/4"	280	143	97	74	52	40	
8" x 8" x 3/8"	248	126	85	65	45	34	
12" x 12" x 3/8"	369	187	126	95	65	50	
16" x 16" x 3/8"	491	248	166	126	85	65	
18" x 18" x 3/8"	552	278	187	141	95	72	
20" x 20" x 3/8"	613	309	207	156	105	80	
24" x 24" x 3/8"	735	369	248	187	126	95	
6" x 24" x 3/8"	296	150	101	77	53	40	
12" x 24" x 3/8"	491	248	166	126	85	65	
6" x 36" x 3/8"	317	161	108	82	56	43	
9" x 36" x 3/8"	443	223	150	114	77	59	
12" x 48" x 3/8"	589	296	199	150	101	77	

^{*}Coverage for 19.4 lb. CEG-Lite is 5% greater than CEG-IG. See coverage chart on our website.

Technical Data

- CEG-IG can be used as both a grout and setting mortar
- Use with virtually any tile: vitreous, semi-vitreous or impervious tile including ceramic, mosaic, quarry, pavers, cement, porcelain, glass, brick, mini-brick, precast terrazzo and natural stone, including green marble
- Use to fill joint widths from 1/16" to 1/2" (1.6 13 mm)
- May be used for both floor or wall installation after tiles have been properly embedded
- Interior applications

Chemical Resistance

28 Day Immersion at 23°C	
Acetic Acid, 10%	Pass
Citric Acid, 50%	Pass
HCI, 36.5%	Pass
Lactic Acid, 10%	Pass
Nitric Acid, 30%	Pass
Oleic Acid 100%	Pass
Phosphoric Acid 80%	Pass
Sulfuric Acid 50%	Pass
Tartaric Acid, 50%	Pass
Tannic Acid 50%	Pass
Potassium Hydroxide, 45%	Pass
Sodium Hydroxide Saturated	Pass
Sodium Hypochlorite, 5%	Pass
Ethanol	Pass
Gasoline	Pass
Methylene Chloride	Fail
Mineral Spirits	Pass
Toluene	Pass
Xylene	Pass
Eco Lab Wash and Walk	Pass
5% Benzoic Acid	Pass
5% Formic Acid	Pass
10% Potassium Permanganate	Pass
Mineral water	Pass
Sea Water	Pass
Methanol	Pass
ipa	Pass
MEK	Pass
Chloroform	Fail
Hydrogen Peroxide	Pass
50% Oleic Acid/Water	Pass

ANSI A118.3 Properties

Property	Test Method	Requirement	Typical Results
Water Cleanability	ANSI 118.3 Section 5.1	>80 minutes	>80 minutes
Initial Set	ASTM C308	>2 hrs	6 hrs
Shrinkage	ASTM C531	<0.25%	0.05%
Sag in Vertical Joint	ANSI 118.3 Section 5.4	No change	No change
Shear Bond to Quarry Tile	ANSI 118.3 Section 5.5	>1000 psi	>1300 psi
Thermal Shock Resistance	ANSI 118.3 Section 5.8	>500 psi	>1300 psi
Compressive Strength	ASTM C579	>3500 psi	9500 psi
Tensile Strength	ASTM C307	>1000 psi	3200 psi

ANSI A118.5 Properties

Property	Test Method	Requirement	Typical Results
Compressive Strength	ASTM C579	>3000 psi	9500 psi
Tensile Strength	ASTM C307	>400 psi	3200 psi
Absorption	ASTM C413	<1%	0%
Modulus of Rupture	ASTM C580	600 psi	7000 psi
Initial Set	ASTM C308	>5 hours	6 hours
Final Set	ASTM C308	<7 days	Pass
Working Time	ASTM C308	10 minutes	40 minutes
Bond Strength	ASTM C321	>150 psi	Pass
Linear Shrinkage	ASTM C531	<1%	0.05%

LEED® is a Registered Trademark of U.S.G.B.C.

©2020 Custom Building Products. All rights reserved. The CUSTOM® logo and select product logos are registered trademarks of Custom Building Products, Inc. CUSTOM may make product modifications at any time without notice. Visit custombuildingproducts.com for updated technical data sheets and SDS information.

Custom Building Products 800-272-8786 custombuildingproducts.com \$\$131 \quad 10/20R

